Bayer MaterialScience

Product Information

DESMOPHEN S-1028-210

Saturated Polyester

Description

Desmophen S-1028-210 is a solvent-free saturated polyester resin.

Application

Desmophen S-1028-210 is a room temperature liquid polyol yielding non-brittle, hard polyurethane coatings where outstanding weatherability, aging and abrasion resistance are needed. As with any product, use of Desmophen S-1028-210 in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

Product Specifications

Property	Value
Solids, wt.%	100
Water content, wt.%	0.05 maximum
Hydroxyl number	195-225
Color, APHA	250 maximum
Acid number	0.1-1.0
Viscosity @ 60ºC;cps	400-600

Typical Properties*

Property	Value
Appearance	clear to light amber liquid
Specific gravity @ 25ºC	1.1
OH content,%	6.4
Weight per gallon, lb. @ 25ºC	9.2
Equivalent wt., avg.(as supplied)	267
Flash point (Cleveland Open Cup)	347ºF(175ºC)

Storage

Desmophen S-1028-210 polyester is hygroscopic. Containers must be kept tightly sealed to prevent contamination with foreign materials and moisture. Undesirable side reactions may occur when contaminated hydroxyl-bearing resins are formulated with polyisocyanates. Recommended storage temperatures for Desmophen S-1028-210 polyester are 32ºF to 122ºF (0-50ºC). The shelf life is twelve months after receipt of material by customer, when stored in closed, original containers at 77ºF (25ºC).

Health and Safety Information

Appropriate literature has been assembled which provides information pertaining to the health and safety concerns that must be observed when handling Desmophen S-1028-210 polyester. For materials mentioned that are not Bayer products appropriate industrial hygiene and other safety precautions recommended by their manufacturer should be followed. Before working with any product mentioned in this publication, you must read and become familiar with available information concerning its hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms such as material safety data sheets and product labels. For further information contact your Bayer MaterialScience representative or the Product Safety and Regulatory Affairs Department in Pittsburgh, Pa.

** These items are provided as general information only. They are approximate values and are not part of the product specifications.*

Note: The information contained in this bulletin is current as of September 2004. Please contact Bayer MaterialScience to determine whether this publication has been revised.

Bayer MaterialScience LLC

100 Bayer Road • Pittsburgh, PA 15205-9741 • Phone: 1-800-662-2927 • www.BayerMaterialScienceNAFTA.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

Sales Offices

17320 Redhill Avenue, Suite 175, Irvine, CA 92614-5660 • 1-949-833-2351 • Fax: 1-949-752-1306
1000 Route 9 North, Suite 103, Woodbridge, NJ 07095-1200 • 1-732-726-8988 • Fax: 1-732-726-1672
2401 Walton Boulevard, Auburn Hills, MI 48326-1957 • Phone: 1-248-475-7700 • Fax: 1-248-475-7701

20162 9/04